



Gemcolite® Ceramic Fiber Wet Insulating Blanket - 2600 Series

Properties & Characteristics

Standards and Options			
Standard Thickness	1/4" to 2" ; other thickness up to 7" available upon request		
Standard Size	24" x 29" , 24" x 36" , 24" x 48" , and 33" x 66" ; other sizes available		
Densities	-LW (14-18 PCF) for most standard applications -MW (22-26 PCF) where a slightly more rigid composition is required -HW (28-32 PCF) for applications requiring rigid and/or abrasion resistant composition		
Properties and Characteristics			
	CD	MD	HD
Color before Firing	Off-White	Off-White	Off-White
Color after Firing	White	White	White
Maximum Use Limit	2600° F (1430°C)	2600° F (1430 C)	2600° F(1430°C)
Melting Point	3260° F (1800°C)	3260° F (1800°C)	3260° F(1800°C)
Typical Chemical Analysis			
	LD	MD	HD
SiO ₂	55%	37%	29%
Al ₂ O ₃	26%	50%	61%
ZrO ₂	15%	10%	7%
Binders/Trace Elements	4%	3%	3%
Approximate Thermal Conductivity			
	Btu • in/hr • ft ² • °F		
Mean Temperature	LD	MD	HD
400° F (205° C)	.36	.52	N/A
800° F (425° C)	.56	.72	.55
1200° F (650° C)	1.02	1.00	.80
1600° F (870° C)	1.34	1.33	1.00
2000° F (1095° C)	2.00	1.82	1.22

Refractory Specialties, Inc. 230 West California Ave. Sebring, Ohio 44672

Tel: 330-938-2101 Email: sales@rsifibre.com Website: www.rsifibre.com