

Microlite

Microlite Material Overview

Microlite is Refractory Specialties Inc's high-efficiency insulation material. It uses a special blend of refractory materials to provide excellent insulation properties where weight or size is critical, or where absolute minimum cold-face temperature is required. Microlite is available in a silica based formulation. It can be used as a loose-fill material, sealed and bagged in a pliable shape, or formed into boards for custom machining, and can be machined on site to meet customer specifications. To answer any questions, or if you have special requirements that aren't covered by this product, call for our expert assistance at (330) 938-2101.

Microlite Technical Information

<u>Property</u>	<u>Microlite Silica</u>
Density	16 lb/ft ³
Modulus of Rupture (MOR)	
Supplied	N/A
After First Use	N/A
Compressive Strength (10% Compression)	22000 lb/ft ²
Maximum Continuous Use Temperature	1800° F
Maximum Suggested Use Temperature	1650° F
Linear Shrinkage	
1800° F	0.5 %
Thermal Conductivity	
400° F	0.20 Btu-in/hr/ft ² /°F
800° F	0.25Btu-in/hr/ft ² /°F
1200° F	0.37 Btu-in/hr/ft ² /°F
1600° F	0.52Btu-in/hr/ft ² /°F
Typical Chemical Analysis (After Use)	
SiO ₂	35 % (By Weight)
Al ₂ O ₃	10 % (By Weight)
Other	55% (By Weight)

Other Information

The information given herein is based on data believed to be reliable; however, Refractory Specialties, Incorporated makes no expressed or implied warranties as to its accuracy and assumes no liability arising out of its use by others. This information does not constitute a license to use or infringe any patents. Further, the data is found to be typical and should not be construed as product specification/s.

Refractory Specialties, Inc. 230 West California Avenue, Sebring, Ohio 44672

Tel: (330) 938-2101/Fax: (330) 938-2574/Web: rsifibre.com /E-mail: @rsifibre.com